

## TECHNICAL DATA SHEET

# UREPAC® RIGID 6 9

### PRODUCT DESCRIPTION

UrePac® Rigid 6 9 is an ultra low density 'open cell' Spray Foam system specifically formulated to provide a foam with a nominal 'applied' core density of 8-10 kg/m<sup>3</sup> (1/2 pound) depending on application parameters. It is formulated for use in commercial / residential wall and ceiling insulation applications where the foam is applied into installed stud work / framed construction. It is to be installed according to the applicable Building Code of Australia regulations and design codes.

### PRODUCT FEATURES

- Over 100 times expansion
- Excellent Acoustic and thermal insulation properties
- 1:1 mix ratio for standard Graco equipment

### UREPAC RIGID 6 9 POLYOL SPECIFICATION


<b>Appearance:</b>	Translucent straw liquid
Specific Gravity (22°C):	1.14 ± 0.02 g/mL
Viscosity (Brookfield) (22°C):	1,000 ± 200 mPa.s

*Spindle 3 Speed 100*

### UREPAC ISO2001 MDI ISOCYANATE SPECIFICATION

<b>Appearance:</b>	Clear brown liquid
Specific Gravity (22°C):	1.23 ± 0.02 g/mL
Viscosity (Brookfield) (22°C):	210 ± 70 mPa.s

*Spindle 1 Speed 50*



## MIXED SYSTEM SPECIFICATION

<b>Mix Ratio:</b>	By Weight	100 Polyol : 120 Isocyanate
	By Volume	100 Polyol : 100 Isocyanate


Test	Specification	Units
<b>Cream Time (22°C):</b> <i>Time from when mixing commences till the liquid starts to expand.</i>	3 ± 1	seconds
<b>String time (22°C):</b> <i>Time from when mixing commences till "strings can be pulled from the surface of the rising foam.</i>	9 ± 2	seconds
<b>Rise time (22°C):</b> <i>Time from when mixing commences till the foam finishes expanding.</i>	12 ± 2	seconds
<b>Free Rise Density (22°C):</b>	15 ± 1	kg/m <sup>3</sup>

*(Obtained from Laboratory 31.5g cup test, results will vary depending on mix quantities)*

## TYPICAL CURED FOAM PROPERTIES

Test	Method	Specification
<b>Core Density:</b>	ASTM D1622	9 ± 1 kg/m <sup>3</sup>
<b>Dimensional Stability (70°C)</b>	+5% Volume (@ 24 hours)	Pass
<b>Closed Cell Content:</b>	ASTM D6226	<20%
<b>Initial K Value:</b>	ASTM C518	0.0360 W/mK
<b>R Value (@ 50mm)</b>	Insulation thickness in meters divided by the K value	1.39
<b>Horizontal Burn</b>	ISO3582	Burn Time: 0 sec Burn Length: 25 mm Burn Rate: 0.4 mm/sec

*After 7 days cure @ 22°C unless otherwise specified.*



## PACKAGING OPTIONS:

Packaging	UrePac Rigid 6 9 Polyol	UrePac ISO2001 MDI Isocyanate
205L Closed Head Drum	<b>220kg</b>	<b>250kg</b>
1000L IBC	<b>1050kg</b>	<b>1250kg</b>

## STORAGE

**POLYOL** should be stored in closed containers under dry conditions out of direct sunlight between 18 and 25°C.

**ISOCYANATE** should be stored separately from the polyol component, but under the same conditions.

Both products will have a minimum shelf life of six months when stored under these conditions.

**CURED PRODUCT:** Like all polyurethanes based on aromatic isocyanates this foam is **not** UV stable and will have surface discolouration and degradation if exposed to UV radiation and sunlight. Please speak to our technical consultants regarding our UV stable coating options if this product is required for use in external applications.

## PROCESSING CONDITIONS:

*All processing conditions are given as a guide only, it is the responsibility of the customer to satisfy themselves that the product is suitable for their requirements by running closely monitored trials prior to production.*


### COMPONENT PREPARATION

**POLYOL** should be mixed or recirculated each day prior to use as the components may separate.

**ISOCYANATE** does not need to be mixed prior to use.

It is recommended that both components should be preconditioned to 22-25°C to ensure that the system will have consistent reactivity and performance, but the drums must be above 10°C before spraying.

Please ensure that the hoses are thoroughly flushed through when changing from closed cell foam to UrePac™ Rigid 6 9 (and back again) as although the polyols do not react with each other, they cause poor quality foam due to contamination with each other.



## MACHINE SETTINGS

Dynamic Spray Pressure: > 1200 psi

*[Note: this is Gun type / setup / output dependant]*

Primary Heater Temperatures: 45 - 50°C

*[set both Component temperatures the same]*

Hose Temperature: as per Primary Heater setting

## SUBSTRATE/SURFACE PREPARATIONS

- the substrate temperature should be a minimum of 18°C to achieve good foam adhesion and effective product yield.
- Do not apply spray foam insulation to damp substrates.
- Check the atmospheric conditions to ensure the temperature of the surface to which the product is to be applied is a minimum of 3°C above the Dew Point at the time of application.
- The product should not be applied in windy conditions due to potential application losses, possible contamination of surrounding areas / surfaces from wind-borne spray and the lack of application control resulting in variable applied thickness and surface evenness / irregularities.
- In internal application situations, protect surrounding surfaces from overspray.
- The product can be applied in temperatures of up to 35°C, so long as Dew Point conditions are met, and the applied thickness and rate of application are controlled.
- In specific temperature and humidity conditions the effects of water vapour 'drive' must be considered in system design and application requirements. This is also important under possible water vapour condensation temperature / humidity conditions.

---

## DISPOSAL

Liquid Systems: Liquid polyol or isocyanates should be disposed of with an EPA approved industrial waste company which meet all applicable federal, state and local laws and regulations.


Cured Urethanes: Fully reacted and cured polyurethanes are inert and can be disposed of as regular landfill.

Container: Dispose of decontaminated drums in accordance with all applicable federal, state and local laws and regulations.

**Do Not Re-use Empty Container.**

**Do Not Cut or Weld Empty Container.**

**WATER CONTAMINATION CAN CAUSES DANGEROUS PRESSURE BUILD UP IN ISOCYANATE DRUMS**



## DISCLAIMER

---

This information is given in good faith but without warranty and is supplied to users based on our general experience and, where applicable, on the results of tests on samples of typical manufacture. However, because of the many factors which are outside our knowledge and control that can affect the use of these products, it is imperative that the end user is satisfied that the material will meet their individual processing and performance requirements. Pacific Urethanes Pty Ltd cannot accept liability for any injury, loss or damage resulting from reliance upon this information.

All sales of this product shall be subject to Pacific Urethanes' Terms and Conditions of Sale. For a copy of these terms please contact us at [info@pacificurethanes.com](mailto:info@pacificurethanes.com).

For additional information, consult the Material Safety Data Sheet for this product.

Revision Number: 01

Revision Date: 26/04/2019

